

ROOF RESTORATION GUIDE

UNGLAZED TERRACOTTA TILES

- Remove and replace broken or cracked tiles and contaminants such as silicone
- If pointing or bedding needs repairing, replace broken or loose ridge caps and re-bed using a 3:1 sand and cement mixture. Allow 24hrs to dry, then apply Roofbond Flexible Pointing as per the instruction on the bucket (10Lt covers approximately 30 ridge caps) to finish off the ridge capping. Allow 24hrs to dry before proceeding to step 3.
- If the roof is moldy, apply Mouldshield C following the directions on the bucket
- With a 3000 psi water pressure hose clean your roof thoroughly. Once you are sure its clean, rinse with a normal hose to ensure all fine residue is washed away.
- Apply one coat of Shieldseal W@ 110m² per 15Lt with an airless spray using 517 tip size.
- Apply two thin coats of Terrabond@ 90-100m² per 15Lt with an airless spray using a 517 tip size.

Head Office

Building 2, 1075 Beaudesert Rd, (Entry via Kerry Rd, Acacia Ridge), Archerfield, QLD 4108

Gold Coast Trade Centre

2/60-64 Kortum drive, Burleigh Heads, QLD 4220

Wangard Trade Centre

6/46 Triumph Ave Wangara, Perth WA 60654108