

METAL ROOF RESTORATION GUIDE

METAL ROOFS - RUST FREE

- With a 3000 psi water pressure hose clean your roof thoroughly. Once you are sure it's clean, rinse with a normal hose to ensure all fine residue is washed away.
- Apply one coat of Shieldseal W Plus@ 150-180m² per 15Lt with an airless spray using a 517 tip size
- Apply two coats of Roofbond@ 80-90m² per 15Lt with an airless sprat using a 521 tip size
- Apply a final coat of NanoProtect SC-96@ 150m² per 15Lt with an airless spray using a 517 tip size
(Increases warranty to 12 years with the first 6 covered for fading and gloss retention)

Head Office

Building 2, 1075 Beaudesert Rd, (Entry via Kerry Rd, Acacia Ridge), Archerfield, QLD 4108

Gold Coast Trade Centre

2/60-64 Kortum drive, Burleigh Heads, QLD 4220

Wangard Trade Centre

6/46 Triumph Ave Wangara, Perth WA 60654108